

June 25, 2009

• **TEST REPORT** •

**PN 85164**

*PO 4965*

**Engineering Department**  
**Coefficient of Friction**

Prepared For:

Mr. Don Delany  
Kellett Enterprises, Inc.  
201 Beverly Road  
Greenville, SC 29609  
Phone: (864) 244-7248  
Fax: (864) 292-8612

Prepared By:   
Edwin Goyzuela  
Staff Engineer

Approved By:   
Mark Centea  
Manager, Engineering

**ISO 9001:2000**  
Registered

ISO 9001:2000 Registered  
Member of ACIL: The American Council of Independent Laboratories

**MEMBER**  
**ACIL**

Letters and reports are for the exclusive use of the clients to whom they are addressed and shall not be reproduced, except in full, without the written permission of Akron Rubber Development Laboratory, Inc. (ARDL). The information contained herein applies to the specific material, products or processes tested or evaluated. No warranty of any kind is herein construed or implied. The liability of ARDL, Inc. shall be limited to the amount of consideration paid for services.

[www.ardl.com](http://www.ardl.com)

2887 Gilchrist Rd. | Akron, Ohio 44305 | [answers@ardl.com](mailto:answers@ardl.com)  
Toll Free (800) 830-ARDL | Worldwide (330) 794-6600 | Fax (330) 794-6610

June 25, 2009

Mr. Don Delany  
Kellett Enterprises, Inc.  
201 Beverly Road  
Greenville, SC 29609  
Phone: (864) 244-7248  
Fax: (864) 292-8612

Page 2 of 2  
PN 85164

**Subject:** Coefficient of Friction Testing

**Received:** One (1) material identified as Vinyl Nitrile, 35 Durometer, Shore A.


**Coefficient Of Friction, ASTM D 1894-99 (Modified):**

Procedure: Two specimens were prepared from the submitted sample by mounting a 2" x 2" section on a steel plate. Each specimen was pulled at 6 in/min. across a section of tile provided by the customer. The sample was loaded with a 200-gram weight.

Results	Vinyl Nitrile, 35 Durometer, Shore A
Static, u	*1.198
Dynamic, u	*1.316

\*The average was reported

Prepared By:

  
Edwin Goyzueta  
Staff Engineer

Approved By:

  
Mark Centea  
Manager, Engineering